



## Coupling Grease

Coupling Grease is a high-performance, polymer-containing lithium grease developed for use in grease-lubricated flexible couplings, such as those commonly found in mining equipment, power plants, manufacturing plants and chemical plants. It has exceptional resistance to oil separation when subjected to the high centrifugal forces typically encountered with medium- and high-speed gear, metallic grid and chain couplings.

Coupling Grease is specifically formulated to the lower (softer) end of the NLGI No. 1 grade to meet most OEM requirements. It is manufactured with high-quality, high-viscosity base oils thickened with lithium 12-hydroxystearate soap. It is fortified with special extreme-pressure (EP) additives, oxidation and corrosion inhibitors and polymers to withstand the centrifugal action in couplings and adhere to the moving parts to provide lubrication, minimize friction and help extend coupling life. It has outstanding performance in the Koppers K36 Centrifugal Oil Separation Test.

### **Applications**

- Gear, metallic grid and flexible-chain couplings
- Couplings commonly used in mining and gas field equipment
- Couplings and universal joints operating under high centrifugal forces
- Couplings used between electric motors and gearboxes in industrial and chemical plants

Coupling Grease meets the requirements of the following industry specifications:

- ANSI/AGMA Standard 9001-B97, Type CG-1 and CG-2 for medium- and high-speed couplings

### **Features/Benefits**

- Outstanding resistance to oil separation
- Excellent oxidation resistance and thermal stability
- Protects against rust and corrosion
- Excellent load-carry ability
- Minimizes friction and wear to help extended coupling life

**High-Performance,  
Extreme-Pressure  
Lithium Grease For  
Industrial Couplings**

### **Contact Information**

**U.S. Customer  
Service:  
1-800-822-6457**

**Technical Hot Line:  
1-877-445-9198**

**International  
Customer Service:  
+1-832-486-3363**

**E-mail address:  
lubricants@  
conocophillips.com**



## Coupling Grease

### Typical Properties

<b>NLGI Grade</b>	<b>0.5/1</b>
Thickener	Lithium
Color	Dark Amber
Dropping Point, °C (°F)	215 (419)
Density, lbs/gal	7.55
Penetration, ASTM D217	
Worked (60 strokes)	335
Worked (10,000 strokes)	305
Texture	Tacky
Four-Ball EP, ASTM D2596, Weld Load, kgf	315
Four-Ball Wear, ASTM D2266, Scar Diameter, mm	0.40
Koppers Centrifugal Oil Separation Test, K36, ASTM D4425	
24 hrs, 50°C, vol %	<2
Oxidation Stability, ASTM D942 100 hrs, Pressure Drop, psi (kPa)	5 (35)
Rust Prevention, ASTM D1743	Pass
Timken OK Load, ASTM D2509, lb	50
Base Oil Properties:	
Viscosity (with polymer),	
cSt @ 40°C	>3,200
cSt @ 100°C	142
Usable Temperature Range,	
°C	-18 to 160
°F	0 to 320

### Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3.conocophillips.com/NetMSDS>.

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

Copyright © 2011 ConocoPhillips Company. The ConocoPhillips logo, Conoco, the Conoco logo, Phillips 66, the Phillips 66 logo, 76 and the 76 logo are trademarks of ConocoPhillips Company in the U.S.A. and other countries.