



Extra Duty Gear Oil

Extra Duty Gear Oil is a premium quality, heavy-duty, extreme-pressure (EP) industrial gear oil developed for the lubrication of heavily loaded enclosed gear drives operating under moderate to severe service conditions. It is specially formulated with “clean gear” additive technology to minimize deposit formation and provide excellent gearbox cleanliness. It is recommended for use in all applications where the equipment manufacturer specifies an AGMA EP gear oil.

Extra Duty Gear Oil is formulated to provide extreme-pressure and antiwear properties, excellent deposit control, protection against rust and corrosion, and resistance to foaming. It has high load-carrying capacity for protection against scuffing and wear. It has excellent oxidation resistance and thermal stability at high temperatures to minimize sludge and varnish formation, and provide long service life. It protects gears and bearings against rust and corrosion. It has excellent water-separating properties to minimize the formation of emulsions, and is resistant to excessive foam buildup that can interfere with proper lubrication.

Extra Duty Gear Oil “M” is specially formulated for use in enclosed gearboxes equipped with mist lubrication systems. It contains a mist suppressant to reduce fogging and stray mist.

Applications

- Enclosed industrial gear drives operating under heavy loads, high peak loads or intermittent shock loads
- Enclosed spur, bevel, helical, herringbone and planetary gear drives where the equipment manufacturer specifies an AGMA EP gear oil
- Heavily loaded plain and rolling-element bearings

Extra Duty Gear Oil meets the requirements of the following industry specifications:

- ANSI/AGMA Standard 9005-E02
- DIN 51517 Part 3, Lubricating Oils, Type CLP
- German Steel Industry SEB 181226, Type CLP
- ISO 12925-1, Type L-CKC
- U.S. Steel 224

**Premium
Extreme-Pressure
Industrial Gear Oil;
Formulated With
“Clean Gear”
Additive Technology**

Contact Information

**U.S. Customer
Service:
1-800-822-6457**

**Technical Hot Line:
1-877-445-9198**

**International
Customer Service:
+1-832-486-3363**

**E-mail address:
lubricants@
conocophillips.com**



Features/Benefits

- High load-carrying capacity for protection against scuffing and wear
- Excellent oxidation resistance and thermal stability
- Excellent deposit control for gearbox cleanliness
- Protects against rust and corrosion
- Fast water separation
- Quick foam release
- Effective mist suppression ("M" grades)

Extra Duty Gear Oil

Typical Properties

ISO Grade	68	100	150	220	220M
AGMA Grade	2 EP	3 EP	4 EP	5 EP	5 EP
Specific Gravity @ 60°F	0.875	0.884	0.880	0.883	0.883
Density, lbs/gal @ 60°F	7.29	7.36	7.33	7.35	7.36
Color, ASTM D1500	3.0	3.5	4.0	4.5	4.0
Flash Point (COC), °C (°F)	235 (455)	235 (455)	243 (469)	252 (486)	243 (469)
Pour Point, °C (°F)	-33 (-27)	-33 (-27)	-33 (-27)	-27 (-17)	-21 (-6)
Viscosity,					
cSt @ 40°C	68.0	100	150	220	220
cSt @ 100°C	8.7	11.1	14.4	18.4	19.0
SUS @ 100°F	353	522	789	1,166	1,163
SUS @ 210°F	55.5	64.3	77.3	94.2	96.8
Viscosity Index	99	98	97	98	96
Acid Number, ASTM D974, mg KOH/g	0.73	0.73	0.73	0.73	0.73
Copper Corrosion, ASTM D130	1a	1a	1a	1a	1a
Four-Ball EP, ASTM D2596, Weld Load, kgf	—	—	250	250	250
Four-Ball Wear, ASTM D4172,					
Scar Diameter, mm	—	—	0.30	0.30	0.30
FZG Scuffing Test, ASTM D5182,					
Failure Load Stage	—	—	>12	>12	>12
Timken OK Load, ASTM D2782, lb	—	—	60	60	60

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

Copyright © 2011 ConocoPhillips Company. The ConocoPhillips logo, Conoco, the Conoco logo, Phillips 66, the Phillips 66 logo, 76 and the 76 logo are trademarks of ConocoPhillips Company in the U.S.A. and other countries.



Extra Duty Gear Oil

Typical Properties

ISO Grade	320	460	460M	680	1000
AGMA Grade	6 EP	7 EP	7 EP	8 EP	8A EP
Specific Gravity @ 60°F	0.891	0.895	0.894	0.911	0.924
Density, lbs/gal @ 60°F	7.42	7.45	7.44	7.59	7.69
Color, ASTM D1500	5.0	5.5	5.5	8.0	8.0
Flash Point (COC),					
°C	254	254	246	>300	>300
°F	489	489	475	>572	>572
Pour Point, °C (°F)	-18 (0)	-18 (0)	-15 (5)	-3 (27)	0 (32)
Viscosity,					
cSt @ 40°C	320	460	460	680	1000
cSt @ 100°C	23.7	30.5	30.4	32.2	39.5
SUS @ 100°F	1,706	2,466	2,466	3,725	5,535
SUS @ 210°F	118	150	149	158	193
Viscosity Index	96	96	96	70	65
Acid Number, ASTM D974, mg KOH/g	0.73	0.73	0.73	0.73	0.73
Copper Corrosion, ASTM D130	1a	1a	1a	1b	1b
Four-Ball EP, ASTM D2596, Weld Load, kgf	250	250	250	250	250
Four-Ball Wear, ASTM D4172,					
Scar Diameter, mm	0.30	0.38	0.38	0.38	0.38
FZG Scuffing Test, ASTM D5182,					
Failure Load Stage	>12	>12	>12	>12	>12
Timken OK Load, ASTM D2782, lb	60	60	60	60	60

Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3.conocophillips.com/NetMSDS>.

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

Copyright © 2011 ConocoPhillips Company. The ConocoPhillips logo, Conoco, the Conoco logo, Phillips 66, the Phillips 66 logo, 76 and the 76 logo are trademarks of ConocoPhillips Company in the U.S.A. and other countries.